

Specification of dipped PP Canvas (belting duck)



No.	Item	Unit	PP 100		PP 125		PP 160		PP 200		PP 300	
			Warp	Weft	Warp	Weft	Warp	Weft	Warp	Weft	Warp	Weft
1	Average breaking strength (min.)	N/mm	130	45	155	55	200	75	240	80	330	85
2	Min. breaking strength	N/mm	120	40	130	45	190	70	230	75	320	80
3	Elongation at 10% load (max. 10 %)	%	1,5		1,5		1,5		1,5		1,5	
4	Breaking Elongation (max.)	%	≥14	≤45	≥14	≤40	≥14	≤40	≥14	≤40	≥14	≤40
5	Hot air shrinkage 150° C × 30 min. (max.)	%	5	0,5	5	0,5	5	0,5	5	0,5	5	0,5
6	Hot air shrinkage difference	%	10		10		10		10		10	
7	Adhension (min.)	N/mm	7,8		7,8		7,8		7,8		7,8	
8	Weight	g/m ²	350 (± 20)		450 (± 20)		600 (± 20)		680 (± 25)		930 (± 30)	
9	Thickness	mm	0,45 (± 0,05)		0,60 (± 0,05)		0,75 (± 0,05)		0,85 (± 0,05)		1,10 (± 0,10)	